

REPORT DOCUMENTATION PAGE

AFRL-SR-BL-TR-01-

0272

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing existing information, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any aspect of the collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 13 Feb. 2001		3. REPORT TYPE AND DATE COVERED Final Technical: 14 Nov. 1997 - 13 Nov. 2000	
4. TITLE AND SUBTITLE Advanced High Temperature Magnetic Materials				5. FUNDING NUMBERS G # F49620-98-1-0098	
6. AUTHOR(S) D.J. Sellmyer, S.S. Jaswal, D.L. Leslie-Pelecky, Y. Liu					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Center for Materials Research and Analysis 111 Brace Laboratory University of Nebraska Lincoln, NE 68588-0113				8. PERFORMING ORGANIZATION REPORT NUMBER 3	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR/NE 801 N. Randolph St., Room 732 Arlington, VA 22203-1977				10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION/AVAILABILITY STATEMENT Distribution Statement A				AIR FORCE OFFICE OF SCIENTIFIC RESEARCH (AFOSR) NOTICE OF TRANSMITTAL DUE TO DISTRIBUTION CODE HAS BEEN REVIEWED AND IS APPROVED FOR PUBLIC RELEASE LAW AFR 190-12. DISTRIBUTION IS UNLIMITED.	
13. ABSTRACT (Maximum 200 Words) Experimental studies on several Sm-Co systems have been carried out in search of improved properties of high-temperature hard-magnet materials. An important result, a record coercivity of 12.3 kOe at 500°C, has been achieved in a Sm-Co-Cu-Ti alloy with a relatively simple annealing procedure. Model calculations are able to explain the increase and then decrease of H_c with temperature. Several other Sm-Co-X and rare earth-Co alloys have been studied through mechanical-milling methods. Self-consistent electronic structure calculations have been made on Nd-Fe compounds and the effects of lattice expansion through hydriding determined.					
14. SUBJECT TERMS high energy product, high temperature magnetic materials, high coercivity, magnetic nanocomposites				15. NUMBER OF PAGES 3	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED		18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED		19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	
20. LIMITATION OF ABSTRACT					

20010430 087

AFOSR Final Technical Report

2. Objectives

The objectives remain as stated in the original proposal.

3. Status of Effort

A significant advance has been made in preparing a Sm-Co-Cu-Ti with excellent hard properties at high temperature ($H_c = 12.3$ kOe at 500°C). This has been reported by "High-Tech Materials Alert," John Wiley & Sons, on May 5, 2000. The significance of the work is that a simple, four-element alloy without Zr substitution can achieve significant properties including a positive change of coercivity with increasing temperature. Additional experimental and theoretical research has given an understanding of exchange-coupled hard magnet materials and their dependence on nanostructure.

4. Accomplishments/New Findings/Highlights

4.1 Electronic Structure Studies of RE-TM Compounds

First-principle studies have been carried out to study the magnetovolume effect in $\text{Nd}_5\text{Fe}_{17}$. Hydrogenation of this compound ($\text{Nd}_5\text{Fe}_{17}\text{H}_{16}$) produces 14.4% volume expansion and increases its Curie temperature and magnetization by 14% and 20% respectively. Calculated results are in good agreement with the experimental data. Calculations also show that 6-7 H atoms per formula unit should produce the maximum increase in T_c of $\sim 34\%$ in this compound.

4.2 Sm-Co-Cu-Ti High-Temperature Permanent Magnets

A class of promising permanent-magnet materials with appreciable high-temperature coercivities has been investigated and an H_c of 12.3 kOe at 500°C obtained. The Sm-Co-Cu-Ti magnets are prepared by arc-melting and require a suitable heat treatment. Magnetization measurements as a function of temperature and x-ray diffraction patterns indicate that the samples are two-phase mixtures of 2:17 and 1:5 structures. Depending on heat treatment and composition, some of the magnets exhibit a positive temperature coefficient of coercivity. The promising high-temperature behavior of the coercivity is ascribed to the temperature dependence of the domain-wall energy, which affects the curvature of the walls and the pinning behavior.

4.3 Mechanically Alloyed High-Temperature Magnets

High temperature magnetic properties of RCO_5 ($\text{R}=\text{Sm}$ and Y) have been studied. The samples were prepared by mechanical alloying and subsequent annealing. X-ray diffraction analysis show that the annealed materials have the hexagonal CaCu_5 structure with 2:17 (or 1:7) regions as a minor phase. Our experimental work shows that SmCo_5 and YCo_5 have nearly the same properties

at temperatures above about 500 °C. This fact, which may lead to the development of rare-earth free high-temperature permanent magnets with moderate energy products, is explained by the negligibly small rare-earth anisotropy contribution at high temperatures.

4.4 Exchange-Coupled Magnets

Much experimental and theoretical work has been done on the magnetism of exchange-coupled nanostructures. First, we have shown in much detail how grain boundaries affect the magnetic behavior of nanostructures. The intergranular interactions, realized by the grain boundaries, is accompanied by a very complicated spin structure in the grains. Second, we have investigated how this intergranular exchange affects the hysteretic behavior of the nanostructures. Depending on grain-boundary structure and grain-size, the calculations yield a variety of cooperative effects which enhance the remanence and make the hysteresis loop more rectangular but also reduce the coercivity. In the weak-coupling regime, the magnetization reversal is determined by non-cooperative localization effects.

5. Personnel Supported and Associated with Project

Faculty: Professors David J. Sellmyer, Sitaram S. Jaswal, Diandra Leslie-Pelecky, Yi Liu, Ralph Skomski, Renat Sabiryanov; Postdoctoral Research Associate: Imaddin A. Al-Omari; Graduate Research Assistants: Jian Zhou and Michael Leonard.

6. AFOSR Publications

Twenty publications have resulted from this grant and another five are accepted for publication.